

Black low VOC 7008/10

May 2015

Technical Data:

Efflux time:	23 s \pm 3 s (DIN 4 mm / 20 °C)
pH value:	8.2 \pm 0.2
Colour strength:	100 % \pm 3 %
Solids:	26.5 % \pm 2 %
Shelf life:	minimum 6 months in sealed containers storage temperature 5–25 °C, keep from freezing, keep from heat!

Resistance Properties:

Formaldehyde:	not coloured
Styrene:	not coloured
Wet Offset:	trace
Wet-Offset 'Strong':	trace
Offset 'Pressed':	no
Light fastness 'Pressed':	WS >7
Light fastness 'Flooring':	recommended
Temperature stability:	220 °C

Use instructions:

Before any receiving inspection and usage, the product has to be thoroughly stirred with a mechanical mixer. Only after this, testing of solid content, color strength and viscosity can be performed properly.

Treat return inks with the appropriate, exact quantity of biocide before putting them on stock. Ensure thorough mixing after addition of biocide.