

White high opacity 8002/10

October 2015

Upon storage, sedimentation may occur due to the low viscosity. However, mixing will normally redisperse the pigment easily. Due to the high pigment content changes of viscosity may occur during storage. In order to avoid possible flocculation, water and extender should be premixed in the correct ratio needed for the intended viscosity and then be added to the ink.

Before any receiving inspection and usage, the product has to be thoroughly stirred with a mechanical mixer. Only after this, testing of solid content, color strength and viscosity can be performed properly.

Treat return inks with the appropriate, exact quantity of biocide before putting them on stock. Ensure thorough mixing after addition of biocide.